



## PRODUCT DATA

### COPO® 1712

COPO®1712 is a general purpose, oil extended SBR made by the cold emulsion process. It is used in applications requiring excellent abrasion resistance, including tires and tread, camelback, and molded and extruded goods. Other Mooney viscosity grades of this product are also available to meet different processing requirements.

**Notice:** All information supplied by or on behalf of Lion Copolymer in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and believed reliable, but Lion Copolymer assumes no liability whatsoever in respect of application, processing or use made of the aforementioned information or products, or any consequence thereof. The buyer undertakes all liability in respect of the application, processing or use of the aforementioned information or product, whose quality and other properties he shall verify, or any consequence thereof. No liability whatsoever shall attach to Lion Copolymer for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of the application, processing or use of the aforementioned information or products by the buyer.

#### Description

23.5% Bound Styrene SBR	100.0 parts
Highly Aromatic Oil	37.5 parts
Stabilizer	Staining
Emulsifier	Mixed Acid
Coagulant	Acid
Specific Gravity	0.95

#### Specifications

Volatile content, % max.	0.75
Organic Acid content, %	4.6 ± 1.40
Oil Content, %	27.1 ± 1.6
Raw Viscosity	42.0 ± 6

#### Rheometer Properties

ML, in-lbs.	2.4 ± 1.0
MH, in-lbs.	12.4 ± 2.0
ts1, minutes	4.0 ± 1.2
t'90, minutes	11.3 ± 2.5

#### Stress Strain Properties, PSI

Tensile	2700 min.
300% Modulus	1350 ± 300
Elongation%	450 min

#### Standard Test Formula

COPO ® 1712	137.50
IRB#7 Carbon Black	68.75
Zinc Oxide	3.00
TBBS	1.38
Sulfur	1.75
Stearic Acid	1.00

#### Test Methods

Volatiles	ASTM D5668
Acid/Oil	ASTM D5774
Raw Mooney Vis	ASTM D1646 MML1+4@100 °C
Rheometer Properties	ASTM D5289 100cpm, 0.5 degree arc, 160 °C, 0 preheat
Stress Strain	ASTM D412 Cured 35' @ 145°C
MIM mix	ASTM D3185-2B

5955 Scenic Highway • Baton Rouge, LA 70805-2044  
800 / 535-9960 • [www.lioncopolymer.com](http://www.lioncopolymer.com)

Copo and Carbomix are registered trademarks of Lion Copolymer, LLC  
C1712 issued 10/10; supersedes all previous