



5955 Scenic Highway • Baton Rouge, LA 70805-2044
800 / 535-9960 • www.lioncopolymer.com

Royalene® Type	Mooney ML(1+4),		Ethylene % ^a	E / P Ratio ^b	Diene %	MWD	Oil phr	Specific Gravity	Product Code
	at 100°C	at 125°C							
DCPD Types									
Royalene 360	48	33	51.0	52 / 48	2.0	Broad	---	0.86	4069083
Royalene 301T	---	40	64.9	67 / 33	3.1	Broad	---	0.87	4069082
Royalene 400	---	37	65.0	67 / 33	3.0	Broad	100	0.88	4051249
RoyalEdge® 4191P	---	24	73.9	75 / 25	1.5	V.Broad	---	0.87	4069237
RoyalEdge® 4191P-1	---	24	73.9	75 / 25	1.5	V.Broad	---	0.87	4069197
RoyalEdge® 4345	---	30	73.9	75 / 25	1.5	V.Broad	---	0.87	4069109
RoyalEdge® 4345F	---	30	73.9	75 / 25	1.5	V.Broad	---	0.87	4069178
Low ENB Types									
Royalene 580-HT	60	39	51.6	53 / 47	2.7	Broad	---	0.86	4069080
Royalene 575	---	60	56.8	58 / 42	2.0	Medium	---	0.86	4033015
Royalene 500	---	56	64.7	66 / 43	2.0	Broad	---	0.86	4015685
Medium ENB Types									
Royalene 511	45	29	54.4	57 / 43	4.6	Medium	---	0.86	4069210
Royalene 563	---	75	57.3	60 / 40	4.5	Medium	---	0.88	4050181
Royalene 512	---	57	65.3	68 / 32	3.9	Medium	---	0.87	4050170
Royalene 694	---	48	66.8	70 / 30	4.5	Medium	75	0.88	4016480
Royalene 697	---	48	66.8	70 / 30	4.5	Medium	100	0.88	4034441
Royalene 556	---	60	67.8	71 / 29	4.5	Medium	---	0.87	4002539
Royalene 868 XE	---	90	67.7	72 / 28	6.0	Medium	---	0.87	4069294
Royalene 5010	---	65	70.7	74 / 26	4.5	Narrow	---	0.86	4069170
Royalene 539	---	70	70.6	74 / 26	4.6	Narrow	---	0.87	4002535
High ENB Types									
Royalene 535	53	33	54.4	60 / 40	9.4	Broad	---	0.86	4069081
Royalene 525	---	65	55.1	60 / 40	8.1	Medium	---	0.86	4016252
Royalene 505	---	55	55.2	60 / 40	8.0	Narrow	---	0.86	4069077
Royalene 547	---	80	56.7	63 / 37	10.0	Medium	---	0.86	4069191
RoyalEdge 4316	---	85	58.6	64 / 36	8.5	V. Broad	---	0.86	4007590
Royalene 645	---	48	60.4	66 / 34	8.5	Narrow	75	0.88	4069076
Royalene 509	---	55	65.3	71 / 29	8.0	Narrow	---	0.87	4004181

^a Ethylene as a percent of total weight

Product Laminate(7).doc

^b Weight ratio of ethylene to propylene

Notice: All information supplied by or on behalf of Lion Copolymer in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and believed reliable, but Lion Copolymer assumes no liability whatsoever in respect of application, processing or use made of the aforementioned information or products, or any consequence thereof. The buyer undertakes all liability in respect of the application, processing or use made of the aforementioned information or product, whose quality and other properties he shall verify, or any consequence thereof. No liability whatsoever shall attach to Lion Copolymer for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of the application, processing or use of the aforementioned information or products by the buyer.